

IN THE CLAIMS:

1. (Previously presented) A filter for removing contaminants from water, said filter comprising:

a first porous filter part comprising an active carbon in a high-molecular low-melt index polymeric binder;

an inlet for directing water to be filtered to the first porous filter part; and

an outlet for directing water filtered by passage through the first porous filter part to a point of use,

wherein the polymeric binder comprises a porous polymer with a melt index of from 1.1 - 2.3 g/10 min (ASTM D1238, 190°C, 15 kg Load),

wherein the active carbon comprises two different particulate active carbons consisting of a) a first particulate active carbon having a larger particle diameter capable of passing through a mesh of 60-100 and b) a second particulate active carbon having a smaller particle diameter capable of passing through a mesh of larger than 100, with the first and second particulate active carbon being mixed in a ratio of 1:4 - 4:1,

wherein the first porous filter part comprises polymeric binder in an amount of 10-25% by weight to active carbon and the first porous filter part has a density of 0.5 - 0.65 g/cm³.

Claim 2 (cancelled).

3. (original) The filter for removing contaminants from water according to claim 1 further comprising a second fibrous filter part comprising a hollow yarn membrane, and the inlet and outlet are arranged so that water to be treated passes from the inlet first through one of the first porous filter part and the second fibrous filter part then through the other of the first porous filter part and the second fibrous filter part and to and through the outlet.

4. (original) The filter for removing contaminants from water according to claim 3 wherein the one of the first porous filter part and second fibrous filter part is the first porous filter part.

5. (previously presented) The filter for removing contaminants from water according to claim 1 wherein the first porous filter has a peripheral surface through which untreated water passes in moving from the inlet towards the outlet.

6. (previously presented) The filter for removing contaminants from water according to claim 1 further comprising a peripheral filtering layer around the first porous filter part through which water to be filtered is passed in moving toward the first porous filter part.

7. (original) The filter for removing contaminants from water according to claim 6 further comprising water-impermeable first and second caps attached in watertight

relationship to the first porous filter part and one of the caps has an opening for discharging water treated by the first porous filter part.

8. (previously presented) The filter for removing contaminants from water according to claim 3 wherein the first porous filter part is located externally of the second fibrous filter part and water to be treated passes from the inlet from a location externally of the first porous filter part to and through the first porous filter part and to and through the second fibrous filter part.

9. (cancelled)

10. (original) The filter for removing contaminants from water according to claim 1 further comprising a second filter part situated so that the first porous filter part and second filter part are located one on top of the other.

11. (original) The filter for removing contaminants from water according to claim 10 wherein the first porous filter part is above the second filter part, the inlet and outlet are arranged so the water to be treated passes from the inlet to the first porous filter part, through the first porous filter part to the second filter part, and through the second filter part to the outlet.

Claims 12 and 13 (cancelled).

14. (original) The filter for removing contaminants from water according to claim 6 wherein the peripheral filtering layer comprises at least one of a fibrous material, a non-woven fabric, and a woven fabric.

15. (original) The filter for removing contaminants from water according to claim 3 wherein the hollow yarn membrane has pores of a size on the order of 0.01 - 5 μm .

16. (original) The filter for removing contaminants from water according to claim 3 wherein the hollow yarn membrane comprises at least one of polyvinyl alcohol, polyacrylonitrile, polyvinyl chloride, polyethylene, polypropylene, 4-methyl-1-pentene, polyester, polyamide, polysulfone, and cellulose derivatives.

17. (previously presented) The filter for removing contaminants from water according to claim 1 further comprising an adaptor for connecting the filter to a tap water faucet.

18. (original) The filter for removing contaminants from water according to claim 1 further comprising a peripheral filter around the first porous filter part through which water to be filtered is passed in moving towards the first porous filter part.

19. (original) The filter for removing contaminants from water according to claim 18 wherein the outlet is defined by a through hole.

20. (currently amended) The filter for removing contaminants from water according to claim 19 further comprising an adaptor for connecting the filter to a conventional tap water faucet.

21. (original) The filter for removing contaminants from water according to claim 1 wherein the filter comprises an outer peripheral surface through which untreated water passes in moving from the inlet towards the outlet.

22. (original) The filter for removing contaminants from water according to claim 1 wherein the first porous filter part has a cylindrical shape.

23. (original) The filter for removing contaminants from water according to claim 6 wherein the peripheral filtering layer has a cylindrical shape.

24. (Previously presented) The filter for removing contaminants from water according to claim 1 wherein the first porous filter part is made by a method comprising the steps of mixing together a) the particulate active carbon and b) the polymeric binder to make a first mixture; placing the first mixture in a mold having a height; vibrating the first mixture so that it has a height in the mold that is 5-15% greater than a desired height for the first porous filter part upon completion thereof; heating the first mixture to fluidize the polymeric binder; pressing the first mixture in the mold to adjust the height of the first mixture in the mold; cooling the first mixture in the mold to complete formation of the first porous filter part; and separating the first porous filter part from the mold.

25.-31. (cancelled).